

ENGLISH	Customer Information
General Information 3M™ ESPE™ Filtek™ P60 Posterior Restorative, is a visible-light activated, radiopaque, restorative composite. It is designed for use in posterior restorations. The filler in Filtek P60 restorative is microfilled. The inorganic filler loading is 61% by volume (without silane treatment) with a particle size range of 0.01 to 3.5 µm. Filtek P60 restorative contains BIS-GMA, UDMA, and BIS-EMA resins. A dental adhesive is used to permanently bond the restoration to the tooth structure. The restorative is available in a variety of shades. It is packaged in individual syringes.	No person is authorized to provide any information which deviates from the information provided in this instruction sheet. Caution: U.S. Federal Law restricts this device to sale or use on the order of a dental professional.
	Warranty 3M ESPE warrants this product will be free from defects in material and manufacture. 3M ESPE MAKES NO OTHER WARRANTIES INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining the suitability of the product for their application. This product is available within the warranty period, you exclusive remedy and 3M ESPE's sole obligation shall be repair or replacement of the 3M ESPE product.
	Limitation of Liability Except where prohibited by law, 3M ESPE will not be liable for any loss or damage arising from this product, whether direct, indirect, special, incidental or consequential, regardless of the theory asserted, including warranty, contract, negligence or strict liability.
	Deutsch
	Precautionary Information for Patients This product contains substances that may cause an allergic reaction by skin contact in certain individuals. Avoid use of this product in patients with known allergic reactions to acrylic resins. If prolonged contact with oral soft tissue occurs, flush with large amounts of water. If allergic reaction occurs, seek medical attention as needed, remove the product if necessary and discontinue future use of the product.
	Precautionary Information for Dental Personnel This product contains substances that may cause an allergic reaction by skin contact in certain individuals. To reduce the risk of allergic response, minimize exposure to these materials. In particular, avoid exposure to uncured product. If skin contact occurs, wash skin with soap and water. Use of protective gloves and a no-touch technique is recommended. Acrylates may penetrate commonly used gloves. If product contacts glove, remove and discard glove, wash hands immediately with soap and water and then re-glove. If allergic reaction occurs, seek medical attention as needed. 3M ESPE MSDS information can be obtained from www.3MESPE.com or contact your local subsidiary.
	Instructions for Use Preparation 1. Prophy: Teeth should be cleaned with pumice and water to remove surface stains. 2. Shade Selection: Before isolating the tooth, select the appropriate shade(s) of restorative material using the Filtek P60 shade guide. 3. Isolation: A rubber dam is the preferred method of isolation. Cotton rolls plus an evacuator can also be used.
	Directions for DIRECT RESTORATIONS 1. Cavity Preparation: Prepare the cavity. Line and point angles should be rounded. No residual amalgam or other base material should be left in the internal form of the preparation that would interfere with light transmission and therefore, the hardening of the restorative material. 2. Pulp Protection: If a pulp exposure has occurred and if the situation warrants a direct pulp capping procedure, use a minimum amount of calcium hydroxide on the exposure following by an application of Vitrebond™ or Vitrebond™ Plus Light Cure Glass Ionomer Liner/Base, manufactured by 3M ESPE. Vitrebond™ liner/base may also be used to line the areas of deep cavity excavation. See Vitrebond liner/base instructions for details. 3. Placement of Matrix: Place a thin dead-soft-mold, or a precontoured-Mylar or a precontoured-metal matrix band and insert wedges firmly. Burnish the matrix band to establish proximal contact and contact area. Adapt the band to seal the gingival area to avoid overhangs. Note: The matrix may be placed following the enamel etching and adhesive application steps if preferred. 4. Adhesive System: Follow the manufacturer's instructions regarding etching, priming, adhesive application and curing.
	5. Dispensing the Composite: Dispense the necessary amount of restorative material from the syringe onto the mix pad by turning the handle slowly in a clockwise manner. To prevent curing of the restorative material when dispensing is completed, turn the handle counterclockwise a half turn to stop paste flow. Immediately replace syringe cap. If not used immediately, the dispensed material should be protected from light.
	6. Placement: 6.1 Place and light cure restoration in increments no thicker than 2.5 mm. 6.2 Slightly overfill the cavity to permit extension of composite beyond cavity margins. Contour and shape with appropriate composite instruments. 6.3 Avoid interset light in the working field. 6.4 Posterior placement hints: a) To aid in placement, the first 1 mm layer may be placed and adapted to the proximal box. b) A condensing instrument (or similar device) can be used to adapt the material to all of the internal cavity aspects.
	7. Curing: This product is intended to be cured by exposure to a halogen or LED light with a minimum intensity of 400mW/cm² in the 400-500 nm range. Cure each increment by exposing its entire surface to a high intensity visible light source, such as 3M ESPE curing light for 20 seconds. Hold the light guide tip as close to the restorative as possible during light exposure.
	8. Finishing: Contour restoration surfaces with fine finishing diamonds, burs or stones. Contour proximal surfaces with Soft-Lex™ Finishing Strips, manufactured for 3M ESPE.
	9. Adjust Occlusion: Check occlusion with a thin articulating paper. Examine centric and lateral excursion contacts. Carefully adjust occlusion by removing material with a polishing diamond or stone.
	10. Polishing: Polish with Soft-Lex Finishing and Polishing System and with white stones or rubber points where discs are not suitable.

Directions for Indirect Procedure For Inlays, Onlays Or Veneers

- Shade selection:** Choose the appropriate shade(s) of Filtek P60 restorative prior to isolation. If the restoration is of sufficient depth, use of an opaque shade is recommended.

- Preparation:** Prepare the tooth.

- Impressioning:** After preparation is complete, make an impression of the prepared tooth by following the manufacturer's instructions of the impressioning material chosen. An impressioning material, such as manufactured by 3M ESPE, may be used.

- Laboratory Procedure**
2.1 Pour the impression of the preparation with the stone. Place pins at the preparation site at this time if a "triple tray" type of impression was used.

- 2.2 Separate the cast from the impression after 45 to 60 minutes. Place pins in die and base the cast as for a typical crown and bridge procedure. Mount or articulate the cast to its counter model to an adequate articulator.

- 2.3 If a second impression was not sent, pour a second cast using the same impression registration. This is to be used as a working model.

- 2.4 Section out the preparation with a laboratory saw and trim away excess or, expose the margins so they can be easily worked. Mark the margins with a red pencil if needed. Add a spacer at this time if one is being used.

- 2.5 Soak the die in water, then with a brush, apply a very thin coat of separating medium to the preparation, let it dry somewhat, then add another thin layer.

- 2.6 Add the first third of composite to the floor of the preparation, stay short of the margins, light cure for 20 seconds.

- 2.7 Add the second third of composite. Allow for the last third (incisal) to include the contact areas, light cure for 20 seconds.

- 2.8 Place the die back into the articulated arch, add the last third of composite to the occlusal surface. Overfill very slightly mesially, distally, and occlusally. This will allow for the mesiodistal contacts and the proper occlusal contact when the opposing arch is brought into occlusion with the uncured incisal composite.

- 2.9 Light cure for only ten seconds, then remove the die to prevent adhering to adjacent surfaces. Finish the curing process.

- 2.10 With the occlusal contacts already established, begin removing the excess composite from around the points of contact. Develop the inclines and ridges as per remaining occlusal anatomy.

- 2.10 Care must be taken when removing the prosthesis from the die. Break off small amounts of the die from around the restoration, then the stone should breakaway cleanly from the cured restoration, until all of the restoration is recovered.

- 2.11 Using the master die, check the restoration for flash, undercuts, and fit. Adjust as necessary, then polish.

- Dental Operatory Procedure**
3.1 Roughen the interior surfaces of the indirect restoration.

- 3.2 Cementation: Cement the prothesis using a 3M ESPE resin cement system by following manufacturer's instructions.

Storage and Use

This product is designed to be used at room temperature. If stored in cool, allow product to reach room temperature prior to use. Shelf life at room temperature is 18 months. Ambient temperatures not exceeding 30°C (86°F) will reduce shelf life. Use outer package for expiration date.

Do not store restorative materials at elevated temperatures or intense light.

Do not store materials in proximity to ongoing contaminating products.

Disinfect the product using an intermediate level disinfection process (liquid contact) as recommended by the Centers for Disease Control and endorsed by the American Dental Association. Guidelines for Infection Control in Dental Health-Care Settings – 2003 (Vol. 52, No. RR-17), Centers for Disease Control and Prevention.

Disposal

Use the Material Safety Data Sheet (available at www.3MESPE.com or through your local subsidiary) for disposal information.

General Information
3M™ ESPE™ Filtek™ P60 Posterior Restorative, is a visible-light activated, radiopaque, restorative composite. It is designed for use in posterior restorations. The filler in Filtek P60 restorative is microfilled. The inorganic filler loading is 61% by volume (without silane treatment) with a particle size range of 0.01 to 3.5 µm. Filtek P60 restorative contains BIS-GMA, UDMA, and BIS-EMA resins. A dental adhesive is used to permanently bond the restoration to the tooth structure. The restorative is available in a variety of shades. It is packaged in individual syringes.

Caution: U.S. Federal Law restricts this device to sale or use on the order of a dental professional.

Warranty
3M ESPE warrants this product will be free from defects in material and manufacture. 3M ESPE MAKES NO OTHER WARRANTIES INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining the suitability of the product for their application. This product is available within the warranty period, you exclusive remedy and 3M ESPE's sole obligation shall be repair or replacement of the 3M ESPE product.

Limitation of Liability
Except where prohibited by law, 3M ESPE will not be liable for any loss or damage arising from this product, whether direct, indirect, special, incidental or consequential, regardless of the theory asserted, including warranty, contract, negligence or strict liability.

Deutsch

Precautionary Information for Patients
This product contains substances that may cause an allergic reaction by skin contact in certain individuals. Avoid use of this product in patients with known allergic reactions to acrylic resins. If prolonged contact with oral soft tissue occurs, flush with large amounts of water. If allergic reaction occurs, seek medical attention as needed, remove the product if necessary and discontinue future use of the product.

Precautionary Information for Dental Personnel
This product contains substances that may cause an allergic reaction by skin contact in certain individuals. To reduce the risk of allergic response, minimize exposure to these materials. In particular, avoid exposure to uncured product. If skin contact occurs, wash skin with soap and water. Use of protective gloves and a no-touch technique is recommended. Acrylates may penetrate commonly used gloves. If product contacts glove, remove and discard glove, wash hands immediately with soap and water and then re-glove. If allergic reaction occurs, seek medical attention as needed.
3M ESPE MSDS information can be obtained from www.3MESPE.com or contact your local subsidiary.

Instructions for Use
Preparation
1. **Prophy:** Teeth should be cleaned with pumice and water to remove surface stains.
2. **Shade Selection:** Before isolating the tooth, select the appropriate shade(s) of restorative material using the Filtek P60 shade guide.
3. **Isolation:** A rubber dam is the preferred method of isolation. Cotton rolls plus an evacuator can also be used.

Directions for DIRECT RESTORATIONS
1. **Cavity Preparation:** Prepare the cavity. Line and point angles should be rounded. No residual amalgam or other base material should be left in the internal form of the preparation that would interfere with light transmission and therefore, the hardening of the restorative material.

2. Pulp Protection: If a pulp exposure has occurred and if the situation warrants a direct pulp capping procedure, use a minimum amount of calcium hydroxide on the exposure following by an application of Vitrebond™ or Vitrebond™ Plus Light Cure Glass Ionomer Liner/Base, manufactured by 3M ESPE. Vitrebond™ liner/base may also be used to line the areas of deep cavity excavation. See Vitrebond liner/base instructions for details.

3. Placement of Matrix: Place a thin dead-soft-mold, or a precontoured-Mylar or a precontoured-metal matrix band and insert wedges firmly. Burnish the matrix band to establish proximal contact and contact area. Adapt the band to seal the gingival area to avoid overhangs.

Note: The matrix may be placed following the enamel etching and adhesive application steps if preferred.

4. Adhesive System: Follow the manufacturer's instructions regarding etching, priming, adhesive application and curing.

5. Dispensing the Composite: Dispense the necessary amount of restorative material from the syringe onto the mix pad by turning the handle slowly in a clockwise manner. To prevent curing of the restorative material when dispensing is completed, turn the handle counterclockwise a half turn to stop paste flow. Immediately replace syringe cap. If not used immediately, the dispensed material should be protected from light.

6. Placement:

6.1 Place and light cure restoration in increments no thicker than 2.5 mm.

6.2 Slightly overfill the cavity to permit extension of composite beyond cavity margins. Contour and shape with appropriate composite instruments.

6.3 Avoid interset light in the working field.

6.4 Posterior placement hints:

a) To aid in placement, the first 1 mm layer may be placed and adapted to the proximal box.

b) A condensing instrument (or similar device) can be used to adapt the material to all of the internal cavity aspects.

7. Curing: This product is intended to be cured by exposure to a halogen or LED light with a minimum intensity of 400mW/cm² in the 400-500 nm range. Cure each increment by exposing its entire surface to a high intensity visible light source, such as 3M ESPE curing light for 20 seconds. Hold the light guide tip as close to the restorative as possible during light exposure.

8. Finishing: Contour restoration surfaces with fine finishing diamonds, burs or stones. Contour proximal surfaces with Soft-Lex™ Finishing Strips, manufactured for 3M ESPE.

9. Adjust Occlusion: Check occlusion with a thin articulating paper. Examine centric and lateral excursion contacts. Carefully adjust occlusion by removing material with a polishing diamond or stone.

10. Polishing: Polish with Soft-Lex Finishing and Polishing System and with white stones or rubber points where discs are not suitable.

Directions for Indirect Procedure For Inlays, Onlays Or Veneers

- Shade selection:** Choose the appropriate shade(s) of Filtek P60 restorative prior to isolation. If the restoration is of sufficient depth, use of an opaque shade is recommended.

- Preparation:** Prepare the tooth.

- Impressioning:** After preparation is complete, make an impression of the prepared tooth by following the manufacturer's instructions of the impressioning material chosen. An impressioning material, such as manufactured by 3M ESPE, may be used.

- Laboratory Procedure**
2.1 Pour the impression of the preparation with the stone. Place pins at the preparation site at this time if a "triple tray" type of impression was used.

- 2.2 Separate the cast from the impression after 45 to 60 minutes. Place pins in die and base the cast as for a typical crown and bridge procedure. Mount or articulate the cast to its counter model to an adequate articulator.

- 2.3 If a second impression was not sent, pour a second cast using the same impression registration. This is to be used as a working model.

- 2.4 Section out the preparation with a laboratory saw and trim away excess or, expose the margins so they can be easily worked. Mark the margins with a red pencil if needed. Add a spacer at this time if one is being used.

- 2.5 Soak the die in water, then with a brush, apply a very thin coat of separating medium to the preparation, let it dry somewhat, then add another thin layer.

- 2.6 Add the first third of composite to the floor of the preparation, stay short of the margins, light cure for 20 seconds.

- 2.7 Add the second third of composite. Allow for the last third (incisal) to include the contact areas, light cure for 20 seconds.

- 2.8 Place the die back into the articulated arch, add the last third of composite to the occlusal surface. Overfill very slightly mesially, distally, and occlusally. This will allow for the mesiodistal contacts and the proper occlusal contact when the opposing arch is brought into occlusion with the uncured incisal composite.

- 2.9 Light cure for only ten seconds, then remove the die to prevent adhering to adjacent surfaces. Finish the curing process.

- 2.10 With the occlusal contacts already established, begin removing the excess composite from around the points of contact. Develop the inclines and ridges as per remaining occlusal anatomy.

- 2.10 Care must be taken when removing the prosthesis from the die. Break off small amounts of the die from around the restoration, then the stone should breakaway cleanly from the cured restoration, until all of the restoration is recovered.

- 2.11 Using the master die, check the restoration for flash, undercuts, and fit. Adjust as necessary, then polish.

- Dental Operatory Procedure**
3.1 Roughen the interior surfaces of the indirect restoration.

- 3.2 Cementation: Cement the prothesis using a 3M ESPE resin cement system by following manufacturer's instructions.

Storage and Use

This product is designed to be used at room temperature. If stored in cool, allow product to reach room temperature prior to use. Shelf life at room temperature is 18 months. Ambient temperatures not exceeding 30°C (86°F) will reduce shelf life. Use outer package for expiration date.

Do not store restorative materials at elevated temperatures or intense light.

Do not store materials in proximity to ongoing contaminating products.

Disinfect the product using an intermediate level disinfection process (liquid contact) as recommended by the Centers for Disease Control and endorsed by the American Dental Association. Guidelines for Infection Control in Dental Health-Care Settings – 2003 (Vol. 52, No. RR-17), Centers for Disease Control and Prevention.

Disposal

Use the Material Safety Data Sheet (available at www.3MESPE.com or through your local subsidiary) for disposal information.

General Information
3M™ ESPE™ Filtek™ P60 Posterior Restorative, is a visible-light activated, radiopaque, restorative composite. It is designed for use in posterior restorations. The filler in Filtek P60 restorative is microfilled. The inorganic filler loading is 61% by volume (without silane treatment) with a particle size range of 0.01 to 3.5 µm. Filtek P60 restorative contains BIS-GMA, UDMA, and BIS-EMA resins. A dental adhesive is used to permanently bond the restoration to the tooth structure. The restorative is available in a variety of shades. It is packaged in individual syringes.

Caution: U.S. Federal Law restricts this device to sale or use on the order of a dental professional.

Warranty
3M ESPE warrants this product will be free from defects in material and manufacture. 3M ESPE MAKES NO OTHER WARRANTIES INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining the suitability of the product for their application. This product is available within the warranty period, you exclusive remedy and 3M ESPE's sole obligation shall be repair or replacement of the 3M ESPE product.

Limitation of Liability
Except where prohibited by law, 3M ESPE will not be liable for any loss or damage arising from this product, whether direct, indirect, special, incidental or consequential, regardless of the theory asserted, including warranty, contract, negligence or strict liability.

Deutsch

Precautionary Information for Patients
This product contains substances that may cause an allergic reaction by skin contact in certain individuals. Avoid use of this product in patients with known allergic reactions to acrylic resins. If prolonged contact with oral soft tissue occurs, flush with large amounts of water. If allergic reaction occurs, seek medical attention as needed, remove the product if necessary and discontinue future use of the product.

Precautionary Information for Dental Personnel
This product contains substances that may cause an allergic reaction by skin contact in certain individuals. To reduce the risk of allergic response, minimize exposure to these materials. In particular, avoid exposure to uncured product. If skin contact occurs, wash skin with soap and water. Use of protective gloves and a no-touch technique is recommended. Acrylates may penetrate commonly used gloves. If product contacts glove, remove and discard glove, wash hands immediately with soap and water and then re-glove. If allergic reaction occurs, seek medical attention as needed.
3M ESPE MSDS information can be obtained from www.3MESPE.com or contact your local subsidiary.

Instructions for Use
Preparation
1. **Prophy:** Teeth should be cleaned with pumice and water to remove surface stains.
2. **Shade Selection:** Before isolating the tooth, select the appropriate shade(s) of restorative material using the Filtek P60 shade guide.
3. **Isolation:** A rubber dam is the preferred method of isolation. Cotton rolls plus an evacuator can also be used.

Directions for DIRECT RESTORATIONS
1. **Cavity Preparation:** Prepare the cavity. Line and point angles should be rounded. No residual amalgam or other base material should be left in the internal form of the preparation that would interfere with light transmission and therefore, the hardening of the restorative material.

2. Pulp Protection: If a pulp exposure has occurred and if the situation warrants a direct pulp capping procedure, use a minimum amount of calcium hydroxide on the exposure following by an application of Vitrebond™ or Vitrebond™ Plus Light Cure Glass Ionomer Liner/Base, manufactured by 3M ESPE. Vitrebond™ liner/base may also be used to line the areas of deep cavity excavation. See Vitrebond liner/base instructions for details.

3. Placement of Matrix: Place a thin dead-soft-mold, or a precontoured-Mylar or a precontoured-metal matrix band and insert wedges firmly. Burnish the matrix band to establish proximal contact and contact area. Adapt the band to seal the gingival area to avoid overhangs.

Note: The matrix may be placed following the enamel etching and adhesive application steps if preferred.

4. Adhesive System: Follow the manufacturer's instructions regarding etching, priming, adhesive application and curing.

5. Dispensing the Composite: Dispense the necessary amount of restorative material from the syringe onto the mix pad by turning the handle slowly in a clockwise manner. To prevent curing of the restorative material when dispensing is completed, turn the handle counterclockwise a half turn to stop paste flow. Immediately replace syringe cap. If not used immediately, the dispensed material should be protected from light.

6. Placement:

6.1 Place and light cure restoration in increments no thicker than 2.5 mm.

6.2 Slightly overfill the cavity to permit extension of composite beyond cavity margins. Contour and shape with appropriate composite instruments.

6.3 Avoid interset light in the working field.

6.4 Posterior placement hints:

a) To aid in placement, the first 1 mm layer may be placed and adapted to the proximal box.

b) A condensing instrument (or similar device) can be used to adapt the material to all of the internal cavity aspects.

7. Curing: This product is intended to be cured by exposure to a halogen or LED light with a minimum intensity of 400mW/cm² in the 400-500 nm range. Cure each increment by exposing its entire surface to a high intensity visible light source, such as 3M ESPE curing light for 20 seconds. Hold the light guide tip as close to the restorative as possible during light exposure.

8. Finishing: Contour restoration surfaces with fine finishing diamonds, burs or stones. Contour proximal surfaces with Soft-Lex™ Finishing Strips, manufactured for 3M ESPE.

9. Adjust Occlusion: Check occlusion with a thin articulating paper. Examine centric and lateral excursion contacts. Carefully adjust occlusion by removing material with a polishing diamond or stone.

10. Polishing: Polish with Soft-Lex Finishing and Polishing System and with white stones or rubber points where discs are not suitable.

Directions for Indirect Procedure For Inlays, Onlays Or Veneers

- Shade selection:** Choose the appropriate shade(s) of Filtek P60 restorative prior to isolation. If the restoration is of sufficient depth, use of an opaque shade is recommended.

- Preparation:** Prepare the tooth.

- Impressioning:** After preparation is complete, make an impression of the prepared tooth by following the manufacturer's instructions of the impressioning material chosen. An impressioning material, such as manufactured by 3M ESPE, may be used.

- Laboratory Procedure**
2.1 Pour the impression of the preparation with the stone. Place pins at the preparation site at this time if a "triple tray" type of impression was used.

- 2.2 Separate the cast from the impression after 45 to 60 minutes. Place pins in die and base the cast as for a typical crown and bridge procedure. Mount or articulate the cast to its counter model to an adequate articulator.

- 2.3 If a second impression was not sent, pour a second cast using the same impression registration. This is to be used as a working model.

- 2.4 Section out the preparation with a laboratory saw and trim away excess or, expose the margins so they can be easily worked. Mark the margins with a red pencil if needed. Add a spacer at this time if one is being used.

- 2.5 Soak the die in water, then with a brush, apply a very thin coat of separating medium to the preparation, let it dry somewhat, then add another thin layer.

- 2.6 Add the first third of composite to the floor of the preparation, stay short of the margins, light cure for 20 seconds.

- 2.7 Add the second third of composite. Allow for the last third (incisal) to include the contact areas, light cure for 20 seconds.

- 2.8 Place the die back into the articulated arch, add the last third of composite to the occlusal surface. Overfill very slightly mesially, distally, and occlusally. This will allow for the mesiodistal contacts and the proper occlusal contact when the opposing arch is brought into occlusion with the uncured incisal composite.

- 2.9 Light cure for only ten seconds, then remove the die to prevent adhering to adjacent surfaces. Finish the curing process.

- 2.10 With the occlusal contacts already established, begin removing the excess composite from around the points of contact. Develop the inclines and ridges as per remaining occlusal anatomy.

- 2.10 Care must be taken when removing the prosthesis from the die. Break off small amounts of the die from around the restoration, then the stone should breakaway cleanly from the cured restoration, until all of the restoration is recovered.

- 2.11 Using the master die, check the restoration for flash, undercuts, and fit. Adjust as necessary, then polish.

- Dental Operatory Procedure**
3.1 Roughen the interior surfaces of the indirect restoration.

- 3.2 Cementation: Cement the prothesis using a 3M ESPE resin cement system by following manufacturer's instructions.

Storage and Use

This product is designed to be used at room temperature. If stored in cool, allow product to reach room temperature prior to use. Shelf life at room temperature is 18 months. Ambient temperatures not exceeding 30°C (86°F) will reduce shelf life. Use outer package for expiration date.

Do not store restorative materials at elevated temperatures or intense light.

Do not store materials in proximity to ongoing contaminating products.

Disinfect the product using an intermediate level disinfection process (liquid contact) as recommended by the Centers for Disease Control and endorsed by the American Dental Association. Guidelines for Infection Control in Dental Health-Care Settings – 2003 (Vol. 52, No. RR-17), Centers for Disease Control and Prevention.

Disposal

Use the Material Safety Data Sheet (available at www.3MESPE.com or through your local subsidiary) for disposal information.

General Information
3M™ ESPE™ Filtek™ P60 Posterior Restorative, is a visible-light activated, radiopaque, restorative composite. It is designed for use in posterior restorations. The filler in Filtek P60 restorative is microfilled. The inorganic filler loading is 61% by volume (without silane treatment) with a particle size range of 0.01 to 3.5 µm. Filtek P60 restorative contains BIS-GMA, UDMA, and BIS-EMA resins. A dental adhesive is used to permanently bond the restoration to the tooth structure. The restorative is available in a variety of shades. It is packaged in individual syringes.

Caution: U.S. Federal Law restricts this device to sale or use on the order of a dental professional.

Warranty
3M ESPE warrants this product will be free from defects in material and manufacture. 3M ESPE MAKES NO OTHER WARRANTIES INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining the suitability of the product for their application. This product is available within the warranty period, you exclusive remedy and 3M ESPE's sole obligation shall be repair or replacement of the 3M ESPE product.

Limitation of Liability
Except where prohibited by law, 3M ESPE will not be liable for any loss or damage arising from this product, whether direct, indirect, special, incidental or consequential, regardless of the theory asserted, including warranty, contract, negligence or strict liability.

Deutsch

